



SUSPENSE

1. SPECIFICATIONS AND FIELDS OF EMPLOYMENT

Precious wall finish for top class interior decoration. SUSPENSE is mouldable, it succeeds in expressing its creativity and manual skill of the decorator, with multidirectional movements, can obtains profound effects of maximum elegance and refinement.

Thanks to the polymeric micro-granule, it contains, the texture obtained takes on an extraordinary and pleasant tactile softness.

SUSPENSE is available in three exclusive variants, which completely cover any furnishing need:

- SUSPENSE SILVER
- SUSPENSE ALUMINUM
- SUSPENSE MATT

Thanks to its characteristics, SUSPENSE guarantees great flexibility use, ranging from elegance in a classic and neoclassical environment to being used in modern-style environments, both in public places and in civil homes. SUSPENSE is non-flammable, it becomes perfectly washable after about three weeks from application.

2. COMPOSITION

Special acrylic emulsion, mix of natural and synthetic biostable micas, polymeric micro-granules, organic and inorganic pigments, additives.

3. APPLICATION PROCEDURES

Preparation of the surface

Sandpaper, dust, fill any imperfections with STUCCOMURO, and apply a coat of FISSATIVO UNIVERSALE appropriately diluted with water in a ratio of 1: 5 up to 1:10 based on the absorption of the support. Allow to dry for at least 4 hours and apply two coats of GENYUS SPECIAL white or the desired colour, up to the total coverage, appropriately diluted (see relative technical data sheet), separated by a minimum of 4-5 hours one from the other.

Spread the first coat of SUSPENSE with DECORA' SPALTER 'on the surface, and perform multidirectional movements, until the desired stylization is obtained.

After 24h give a second layer of SUSPENSE to obtain the final effect that will occur after drying, or 4-5 hours after application.

4. TECHNICAL DATA

SPECIFIC WEIGHT:

SUSPENSE SILVER: $1,03 \pm 5\%$ Kg./Lt.

SUSPENSE ALLUMINIO: $1,03 \pm 5\%$ Kg./Lt.

SUSPENSE MATT: $1,101 \pm 5\%$ Kg./Lt.

COLOURS: From the colour chart, The colours can also be obtained through the tinting system

GLOBAL TINTING SYSTEM

VISCOSITY': Thixotropic

COVERAGE : 10 m²/Lt. per coat.

DILUTION: 10% in volume with water

PACKAGE: Polyethylene Lt. 2,5

DRYING to touch: 1 hours at 20°C.

DRYING Completely: 24 hours at 20°C.

APPLICATION TEMP: between 7°C and 30°C.

APPLICATION: Brush or Spray

PRESERVATION: 24 months in the intact packages away from temperature changes.

HS-CODE: 32091000

5. ITEM OF SPECIFICATIONS

Decoration of interior wall surfaces with perfectly washable acrylic finish of the SUSPENSE type of SPIVER S.r.l. applied and finished with a special SPALTER PER DECORA 'type brush by SPIVER S.r.l. Price including material and installation, excluding scaffolding per m² €

NB The above-mentioned data are susceptible of variations. Spiver Ltd. is not responsible for any negative result depending on the application of the product out of the Company's control and on the agents unrelated to the product quality

Application



Emotion with paint ...

SPIVER s.r.l.

contrada Babbaurra S.S. 122

93100 Caltanissetta (CL)

Tel. +39 0934 57 77 91 Fax +39 0934 58 87 95

www.spiver.it - info@spiver.it

Scheda Tecnica: Suspense SP 130. Rev.1 La presente scheda annulla e sostituisce le precedenti